

Stone Testing Results

4-23-07

AET Project # 05-03101

Door County Custom Stone

1. Density and Absorption, ASTM: C97
 - A. Absorption = 0.44
 - B. Specific Gravity = 2.77
2. Compressive Strength, ASTM:C170
Average = 13550 psi
3. Modulus of Rupture, ASTM C99
Average = 2600 psi
4. Flexural Strength, ASTM:C880
Average = 1575 psi